



<b>FICHE TECHNIQUE</b>		
<b>CHARBON ACTIF GRANULÉ À BASE D'HOUILLE</b>		
<b>Iodine Adsorption value ( Mg/g )</b>	500-600	700-800
<b>Specific surface area ( m2/g)</b>	980	1020
<b>Hardness ( % )</b>	98	99
<b>Ash ( % )</b>	<5	<5
<b>Loading density ( g/l)</b>	600-650	550-600
<b>Moisture ar %</b>	<5	<5
<b>Mesh Size</b>	As required	