



FICHE TECHNIQUE CHARBON ACTIF EN POUDRE À BASE D'HOUILLE	
Methylene Blue Adsorption (mg/gm)	90-110
Fixed Carbon Content (%)	38-42
Ash (%)	<45
Volatile Matter (%)	3.46
Moisture (%)	5
pH	8.5
Mesh Practice Size	90% passing through 200 mesh